

SOUTHWEST RESEARCH INSTITUTE®

6220 CULEBRA ROAD 78238-5166 • P.O. DRAWER 28510 78228-0510 • SAN ANTONIO, TEXAS, USA • (210) 684-5111 • WWW.SWRI.ORG

CHEMISTRY AND CHEMICAL ENGINEERING DIVISION

FIRE TECHNOLOGY DEPARTMENT
WWW.FIRE.SWRI.ORG
FAX (210) 522-3377



FIRE PERFORMANCE EVALUATION IN ACCORDANCE WITH ASTM E136-19, STANDARD TEST METHOD FOR BEHAVIOR OF MATERIALS IN A VERTICAL TUBE FURNACE AT 750 °C

MATERIAL ID: *Aluminum Alloy 6005A*

FINAL REPORT
Consisting of 4 Pages

SwRI® Project No.: 01.24921.01.311b
Test Date: April 21, 2020
Report Date: May 15, 2020

Prepared for:

The Aluminum Association
1400 Crystal Drive
Suite 430
Arlington, VA 22202

NA Submitted by:

Approved by:

Eugene F. Horton
Principal Engineering Technologist
Material Flammability Section

Matthew S. Blais, Ph.D.
Director
Fire Technology Department

This report is for the information of the client. It may be used in its entirety for the purpose of securing product acceptance from duly constituted approval authorities. This report shall not be reproduced except in full, without the written approval of SwRI. Neither this report nor the name of the Institute shall be used in publicity or advertising.



Benefiting government, industry and the public through innovative science and technology

1.0 INTRODUCTION

This report describes a small-scale fire test conducted on a material in accordance with ASTM E136-19, *Standard Test Method for Behavior of Materials in a Vertical Tube Furnace at 750 °C*, for The Aluminum Association located in Arlington, Virginia. Testing was conducted on April 21, 2020, at the Fire Technology Department of Southwest Research Institute (SwRI), located in San Antonio, Texas.

The results presented in this report apply specifically to the specimens tested, in the manner tested, and not to the entire production of these or similar materials, nor to the performance when used in combination with other materials.

2.0 DESCRIPTION OF TEST APPARATUS AND PROCEDURE

The ASTM E136-19 hot-air ignition furnace consists primarily of an electrical heating unit and specimen holder. The furnace tube is a vertical tube, with an inside diameter of 100 ± 5 mm and a length of 230 ± 20 mm, made of ceramic that will withstand at least 750 °C. The inner ceramic tube, with an inside diameter of 75 ± 5 mm, a length of 230 ± 20 mm, and a thickness of approximately 3 mm, is placed inside the furnace tube and positioned 20 ± 2 mm above the furnace floor on spacer blocks. The test apparatus is shown in Figure 1.

The air temperature inside the furnace is stabilized to 750 °C prior to testing. Sheathed thermocouples are used to measure the temperature of the furnace air (T_2), specimen surface (T_4), and specimen center (T_3). The duration of flaming is recorded during the test, and specimen mass loss is determined based on weight measurements before and after testing. ASTM E136-19 requires that a series of four tests be conducted for each sample.

A material passes if at least three of the four specimens tested meet the following criteria (The three specimens do not need to meet the same condition.):

1. When the weight loss is 50% or less:
 - a. The recorded temperatures of the surface and interior thermocouples do not at anytime during the test rise more than 30 °C (54°F) above the stabilized furnace temperature measured at T_2 prior to the test.
 - b. No sustained flaming after the first 30 s of the test.
2. When the weight loss is 50% or more:
 - a. The surface and interior thermocouples cannot exhibit any temperature rise from the stabilized temperature measured by the interior thermocouple before testing.
 - b. No flaming at any time during the test.

3.0 DESCRIPTION OF TEST SPECIMENS

The test samples were received by SwRI on April 13, 2020. The samples were placed in a controlled environment maintained at $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ($73\text{ }^{\circ}\text{F} \pm 5\text{ }^{\circ}\text{F}$) and $50\% \pm 5\%$ relative humidity from the time they were received. Prior to testing, the specimens were prepared according to the ASTM E136 standard and then placed in an oven at $60\text{ }^{\circ}\text{C}$ for 24 h, then placed in a desiccator to cool at room temperature. A more detailed description of the material can be found in Table 1.

Table 1. Test Sample Description.

Material ID	Description of Material	Tested Nominal Dimensions*	Average Tested Mass*	Nominal Density	Color
<i>Aluminum Alloy 6005A</i>	Labeled 6005A	$38 \times 38 \times 50\text{ mm}$	215.30 g	2.7 g/cm^3	Gray

* Measured by SwRI personnel.

4.0 TEST RESULTS

Testing was conducted on April 21, 2020. Tabular test data and graphs of the measured temperatures plotted with respect to time are presented at the end of this report.

5.0 CONCLUSIONS

The material identified as *Aluminum Alloy 6005A*, meets the requirements of the ASTM E136-19 standard.

SOUTHWEST RESEARCH INSTITUTE
ASTM E 136 TEST DATA SHEET

Client: The Aluminum Association
Operator: Nathan W.
Test Date(s): April 21, 2020
Material ID:* Aluminum alloy 6005A
Description:* Labeled 6005A

Receipt Date: April 13, 2020
Color: Gray*
Average Sample Mass: 215.30 g

* Information/instructions provided by the Client

RESULTS

Run	Initial Mass (g)	Final Mass (g)	Percent Mass Loss	Specimen Center				Specimen Surface			
				Stabilized (°C)	Maximum (°C)	Δ T (°C)	Criteria* ΔT < 30 °C	Stabilized (°C)	Maximum (°C)	Δ T (°C)	Criteria* ΔT < 30 °C
1	215.11	215.09	0%	749	723	-26	Pass	749	721	-28	Pass
2*	215.48	215.42	0%	751	725	-26	Pass	751	723	-28	Pass
3	217.20	217.19	0%	751	723	-28	Pass	751	723	-28	Pass
4	213.28	193.21	9%	749	716	-33	Pass	749	716	-33	Pass


*Criteria for when percent mass loss < 50%

TEST OBSERVATIONS

Run	Insertion Time (s)	Ignition Time (min:s)	Flameout (min:s)	Duration of flaming (min:s)	Criteria: No flaming after first 30 s	Observed Smoke (min:s)	Observed Soot (min:s)	Total Test Time (s)
1	56	-	-	-	Pass	No	No	1800
2*	42	-	-	-	Pass	No	No	1800
3	32	-	-	-	Pass	No	No	1800
4	31	-	-	-	Pass	No	No	1800

* Test prematurely ended due to sample issue

Center Temperature Graph



Surface Temperature Graph

